



Bar Reinforced Molded Lumber



Tangent's Bar Reinforced Molded Lumber is an exceptionally strong and durable product, best suited for projects that require wider spans and dimensional stability. Able to withstand even the most extreme weather conditions and environments, Bar Reinforced Molded Lumber remains long-lasting in light and heavy-duty structural applications.


COMMON APPLICATIONS

- Playgrounds
- Retaining Walls
- Pedestrian Bridges
- Fencing
- Dock Piles
- Dock-Substructure
- Boardwalk - Decking
- Boardwalk - Substructure


STANDARD COLORS



Black



Brown



Spice



Mink



Redwood



Cedar



Chestnut



Norwegian Weatherwood



White



Cement



Gray



Dark Gray



Industrial Gray



Blue



Yellow



Green

TECHNICAL INFORMATION

| Properties | ASTM | Value/Units |
|--|-------|---------------------|
| Specific Gravity | D6111 | 0.99 |
| Flexural Strength | D6109 | 2,700 - 9,500 psi* |
| Flexural Modulus (Secant, at 1% strain) | D6109 | 270 - 725 ksi* |
| Compressive Strength (Perpendicular to grain) | D6108 | 1,482 psi |
| Compressive Modulus (Perpendicular to grain, Secant, at 1% strain) | D6108 | 50 ksi |
| Coefficient of Thermal Expansion | D6341 | 0.000014 in/in/°F |
| Static Coefficient of Friction - Dry | D2047 | 0.72 |
| Impact Resistance (Izod) | D256 | 2.64 ft-lb/in |
| Water Absorption | D570 | 0.27% max by weight |
| Screw Withdrawal | D6117 | 646 lbs |
| Useful Temperature Range | | -40F to +140°F |

*Dependent upon selected profile and reinforcement

Suitability and Limitations

These products have greater impact resistance than wood but conversely less rigidity, and therefore prior to use a thorough design engineering study must be performed to determine the suitability of Bar Reinforced Molded Lumber in any critical application.

Fabrication is similar to wood and normal woodworking tools can be used. One should be advised that by transforming the product by drilling holes and routing edges the integrity and strength of the part can be altered. Eye protective wear, dusk masks, gloves and normal safety precautions must be used when handling and fabricating the product. (See MSDS sheet for more details)

Inherent in Bar Reinforced Molded Lumber products, you will observe a greater coefficient of thermal expansion than stiffer wood products. Therefore, when designing your application, an accommodation must be made to properly allow for expected expansion and contraction over the length of the product.

Static electricity is a naturally occurring phenomenon to all resin based products. On extremely dry days there is the potential to experience a small static shock if you walk across a Bar Reinforced Molded Lumber product and touch a conducting surface such as a metal fixture. This is comparable to walking across your carpet and receiving a static shock when you touch the door handle. We do not warranty against static electricity as it is a natural occurring phenomenon and is not a manufacturing defect.

During winter conditions, you might find any surface made from Bar Reinforced Molded Lumber to be slippery in snow, wet and frost conditions. Unlike most other surfaces, you can easily spread rock salt or calcium chloride to restore decent traction and melt the frost or ice layer with no harmful effect to the Bar Reinforced Molded Lumber products.

Warranty

Tangent Technologies LLC, the manufacturer of Bar Reinforced Molded Lumber products, offers a limited warranty that this product will not rot, splinter, decay or suffer structural damage directly from termites or fungal decay under normal use. Tangent Technologies LLC does not recommend or approve this product for all end use applications. The appropriate national and local code authorities should be consulted for safety, suitability and applicability for intended use prior to purchasing product. (See full warranty details)

This guideline and summary is intended to provide the distributor, installer and end user with basic guidelines and technical specifications for designing and properly installing the Bar Reinforced Molded Lumber products. However, the installer and/or purchaser of any Bar Reinforced Molded Lumber product is solely responsible for interpreting specific job conditions and determining the engineering design and suitability of end use and application of any Bar Reinforced Molded Lumber product. Adherence to applicable building and safety codes for specific locations and applications of this product are the sole responsibility of the installer and/or purchaser. In no event shall Tangent Technologies LLC, the manufacturer of the Bar Reinforced Molded Lumber products, be liable for labor, installation, reinstallation or for any indirect, punitive, exemplary or consequential damages of any kind whatsoever from the provisions of this information.

This revision 1.6 [9/6/22] supersedes all other Bar Reinforced Molded Lumber technical data sheets.