

Bar Reinforced Lumber




Manufactured as a high-strength structural product, Tangent's Bar Reinforced Lumber is well-suited for exterior applications where increased support or load bearing is required. Engineered from HDPE plastic, UV inhibitors and strengthening fibers, Tangent's Bar Reinforced Lumber will look new for years and last for decades.


Common Applications

- Fender Piles
- Fender Wales
- Bulkheads
- Retaining Walls
- Dolphin Pile Clusters
- Pedestrian Bridges
- Boardwalk Substructure
- Light Duty Load Bearing Piles


Standard Colors



Tudor Brown



Milwaukee Brown




Cedar



Weathered Wood



Cherrywood



Patriot Blue



Turf Green




Sand




Gray



Light Gray



Black



Bright White



Redwood

TECHNICAL INFORMATION

Properties	ASTM	Value/Units
Specific Gravity	D792	48.0 lb/cubic ft
Flexural Strength	D6109	2,300 - 10,300 psi*
Flexural Modulus (Secant, at 1% strain)	D6108	200,000 - 1,000,000 psi*
Compressive Strength (Perpendicular to grain)	D6108	3,169 psi
Compressive Modulus (Perpendicular to grain, Secant, at 1% strain)	D6108	200,293 psi
Coefficient of Thermal Expansion	D6341	0.0000281 in/in/F
Static Coefficient of Friction - Dry	D2047	0.73
Impact Resistance (Izod)	D256	4.53 ft-lb/in
Water Absorption	D570	<0.1% in 24 hrs.
Screw Withdrawal	D6117	703 lbs
Useful Temperature Range		-40F to +140F

*value dependent upon profile and reinforcement, please contact to learn more

Suitability and Limitations

These products have greater impact resistance than wood but conversely less rigidity, and therefore prior to use a thorough design engineering study must be performed to determine the suitability of Bar Reinforced Lumber in any critical application.

Fabrication is similar to wood and normal woodworking tools can be used. One should be advised that by transforming the product by drilling holes and routing edges the integrity and strength of the part can be altered. Eye protective wear, dusk masks, gloves and normal safety precautions must be used when handling and fabricating the product. (See MSDS sheet for more details)

Inherent in Bar Reinforced Lumber products, you will observe a greater coefficient of thermal expansion than stiffer wood products. Therefore, when designing your application, an accommodation must be made to properly allow for expected expansion and contraction over the length of the product.

Static electricity is a naturally occurring phenomenon to all resin based products. On extremely dry days there is the potential to experience a small static shock if you walk across a Bar Reinforced Lumber product and touch a conducting surface such as a metal fixture. This is comparable to walking across your carpet and receiving a static shock when you touch the door handle. We do not warranty against static electricity as it is a natural occurring phenomenon and is not a manufacturing defect.

During winter conditions, you might find any surface made from Bar Reinforced Lumber to be slippery in snow, wet and frost conditions. Unlike most other surfaces, you can easily spread rock salt or calcium chloride to restore decent traction and melt the frost or ice layer with no harmful effect to the Bar Reinforced Lumber products.

Warranty

Tangent Technologies LLC, the manufacturer of Bar Reinforced Lumber products, offers a limited warranty that this product will not rot, splinter, decay or suffer structural damage directly from termites or fungal decay under normal use. Tangent Technologies LLC does not recommend or approve this product for all end use applications. The appropriate national and local code authorities should be consulted for safety, suitability and applicability for intended use prior to purchasing product. (See full warranty details)

This guideline and summary is intended to provide the distributor, installer and end user with basic guidelines and technical specifications for designing and properly installing the Bar Reinforced Lumber products. However, the installer and/or purchaser of any Bar Reinforced Lumber product is solely responsible for interpreting specific job conditions and determining the engineering design and suitability of end use and application of any Bar Reinforced Lumber product. Adherence to applicable building and safety codes for specific locations and applications of this product are the sole responsibility of the installer and/or purchaser. In no event shall Tangent Technologies LLC, the manufacturer of the Bar Reinforced Lumber products, be liable for labor, installation, reinstallation or for any indirect, punitive, exemplary or consequential damages of any kind whatsoever from the provisions of this information.

This revision 1.6 [4/5/22] supersedes all other Bar Reinforced Lumber technical data sheets.