



Fiber Reinforced Lumber




Tangent's Fiber Reinforced Lumber is a structural product engineered with fiberglass strands to increase strength and rigidity. Best-suited for projects requiring a wider span and dimensional stability, this recycled plastic lumber product is ideal for many types of commercial and structural applications.


COMMON APPLICATIONS

- Boardwalks
- Playground Equipment
- Stadium Seating
- Park Benches & Picnic Tables
- Fencing
- Retaining Walls
- Cribbing
- Commercial Boat
- Decking


STANDARD COLORS




Tudor Brown




Milwaukee Brown



Cedar



Weathered Wood




Cherrywood




Patriot Blue



Turf Green




Sand



Gray



Light Gray



Black



Bright White



Redwood

TECHNICAL INFORMATION

Properties	ASTM	Value/Units
Specific Gravity	D6111	48.0 lb/cubic ft
Flexural Strength	D6109	2,114 psi
Flexural Modulus (Secant, at 1% strain)	D6109	137,861 psi
Compressive Strength (Perpendicular to grain)	D6108	1,440 psi
Compressive Modulus (Perpendicular to grain, Secant, at 1% strain)	D6108	70,000 psi
Coefficient of Thermal Expansion	D6341	0.000028 in/in/°F
Static Coefficient of Friction - Dry	D2047	0.75 average
Static Coefficient of Friction - Wet	D2047	0.84 average
Impact Resistance (Izod)	D256	4.53 ft-lb/in
Water Absorption	D570	<0.1% in 24 hrs
Screw Withdrawal	D6117	703 lbs
Useful Temperature Range		-40F to +140F

All above values shall be considered average except flexural strength. This value must have appropriate reduction factors set by the engineer of record.

Suitability and Limitations

These products have greater impact resistance than wood but conversely less rigidity, and therefore prior to use a thorough design engineering study must be performed to determine the suitability of Fiber Reinforced Lumber in any critical application.

Fabrication is similar to wood and normal woodworking tools can be used. One should be advised that by transforming the product by drilling holes and routing edges the integrity and strength of the part can be altered. Eye protective wear, dusk masks, gloves and normal safety precautions must be used when handling and fabricating the product. (See SDS sheet for more details)

Inherent in Fiber Reinforced Lumber products, you will observe a greater coefficient of thermal expansion than stiffer wood products. Therefore, when designing your application, an accommodation must be made to properly allow for expected expansion and contraction over the length of the product.

Static electricity is a naturally occurring phenomenon to all resin based products. On extremely dry days there is the potential to experience a small static shock if you walk across a Fiber Reinforced Lumber product and touch a conducting surface such as a metal fixture. This is comparable to walking across your carpet and receiving a static shock when you touch the door handle. We do not warranty against static electricity as it is a natural occurring phenomenon and is not a manufacturing defect.

During winter conditions, you might find any surface made from Fiber Reinforced Lumber to be slippery in snow, wet and frost conditions. Unlike most other surfaces, you can easily spread rock salt or calcium chloride to restore decent traction and melt the frost or ice layer with no harmful effect to the Fiber Reinforced Lumber products.

Warranty

Tangent Technologies LLC, the manufacturer of Fiber Reinforced Lumber products, offers a limited warranty that this product will not rot, splinter, decay or suffer structural damage directly from termites or fungal decay under normal use. Tangent Technologies LLC does not recommend or approve this product for all end use applications. The appropriate national and local code authorities should be consulted for safety, suitability and applicability for intended use prior to purchasing product. (See full warranty details)

This guideline and summary is intended to provide the distributor, installer and end user with basic guidelines and technical specifications for designing and properly installing the Fiber Reinforced Lumber products. However, the installer and/or purchaser of any Fiber Reinforced Lumber product is solely responsible for interpreting specific job conditions and determining the engineering design and suitability of end use and application of any Fiber Reinforced Lumber product. Adherence to applicable building and safety codes for specific locations and applications of this product are the sole responsibility of the installer and/or purchaser. In no event shall Tangent Technologies LLC, the manufacturer of the Fiber Reinforced Lumber products, be liable for labor, installation, reinstallation or for any indirect, punitive, exemplary or consequential damages of any kind whatsoever from the provisions of this information.

This revision 1.6 [1/12/23] supersedes all other Fiber Reinforced Lumber technical data sheets.